

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
24 February 2005 (24.02.2005)

PCT

(10) International Publication Number  
**WO 2005/017059 A2**

(51) International Patent Classification<sup>7</sup>: **C09J 7/00**

(21) International Application Number:  
PCT/US2004/020326

(22) International Filing Date: 24 June 2004 (24.06.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
2003-206343 6 August 2003 (06.08.2003) JP

(71) Applicant (for all designated States except US): **3M INNOVATIVE PROPERTIES COMPANY** [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **SHINOHARA, Masaru** [JP/JP]; 8-8 Minami-Hashimoto 3-chome, Sagamihara-city, Kanagawa 229-1185 (JP). **KIM, Yoong** [SG/SG]; 100 Woodlands 7, Singapore 738205 (SG). **TAKAMATSU, Yorinobu** [JP/JP]; 8-8 Minami Hashimoto 3-chome, Sagamihara-city, Kanagawa 229-1185 (JP). **USHITO, Harumi** [JP/JP]; 8-8 Minami-Hashimoto 3-chome, Sagamihara-city, Kanagawa 229-1185 (JP).

(74) Agents: **BARDELL, Scott, A.** et al.; Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: HEAT RESISTANT MASKING TAPE



(57) Abstract: A heat resistant masking tape, comprising (1) a heat resistant backing film layer; and (2) a pressure-sensitive adhesive layer disposed on the heat resistant backing film layer, wherein the pressure-sensitive adhesive

layer comprises a polymer resulting from polymerizing and cross-linking a monomer mixture comprising an alkyl (meth)acrylate with an alkyl group having 4 to 15 carbon atoms, glycidyl (meth)acrylate and (meth)acrylic acid, the glycidyl (meth)acrylate being present in an amount of 2 to 13% by weight of the total weight of monomers and the (meth)acrylic acid being present in an amount of 1 to 7% by weight of the total weight of monomers.

WO 2005/017059 A2

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
24 February 2005 (24.02.2005)

PCT

(10) International Publication Number  
**WO 2005/017059 A3**

(51) International Patent Classification<sup>7</sup>: **C09J 7/02**

(21) International Application Number:  
PCT/US2004/020326

(22) International Filing Date: 24 June 2004 (24.06.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
2003-206343 6 August 2003 (06.08.2003) JP

(71) Applicant (for all designated States except US): **3M INNOVATIVE PROPERTIES COMPANY** [US/US];  
3M Center, Post Office Box 33427, Saint Paul, Minnesota  
55133-3427 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **SHINOHARA, Masaru** [JP/JP]; 8-8 Minami-Hashimoto 3-chome, Sagamihara-city, Kanagawa 229-1185 (JP). **KIM, Yoong** [SG/SG]; 100 Woodlands 7, Singapore 738205 (SG). **TAKAMATSU, Yoronobu** [JP/JP]; 8-8 Minami Hashimoto 3-chome, Sagamihara-city, Kanagawa 229-1185 (JP). **USHITO, Harumi** [JP/JP]; 8-8 Minami-Hashimoto 3-chome, Sagamihara-city, Kanagawa 229-1185 (JP).

(74) Agents: **BARDELL, Scott, A.** et al.; Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).


**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the international search report:  
14 April 2005

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: HEAT RESISTANT MASKING TAPE



(57) Abstract: A heat resistant masking tape, comprising (1) a heat resistant backing film layer; and (2) a pressure-sensitive adhesive layer disposed on the heat resistant backing film layer, wherein the pressure-sensitive adhesive layer comprises a polymer resulting from polymerizing and

cross-linking a monomer mixture comprising an alkyl (meth)acrylate with an alkyl group having 4 to 15 carbon atoms, glycidyl (meth)acrylate and (meth)acrylic acid, the glycidyl (meth)acrylate being present in an amount of 2 to 13% by weight of the total weight of monomers and the (meth)acrylic acid being present in an amount of 1 to 7% by weight of the total weight of monomers.

WO 2005/017059 A3